

**Library of Congress Preservation Directorate**  
**Specification Number 200-224 – 11**  
**Specifications for Expansion Folders with Reinforced Tab**  
**For the Storage of Artifacts**

This specification is provided as a public service by the Preservation Directorate of the Library of Congress. Any commercial reproduction that implies endorsement of a product, service, or materials, in any publication, is strictly prohibited by law. This Specification is written for L.C. purchasing purposes and is subject to change when necessary. If you are reading a paper copy of this specification please check our website for the most up-to-date version.

---

## **1. Composition and Chemical Requirements**

### **1.1 Fiber**

The stock must be made from rag or other high alpha-cellulose content pulp, minimum of 87%, as defined in ISO 18902. It must not contain any post consumer waste recycled pulp.

### **1.2 Lignin**

The stock must give a negative reading for lignin as determined by the phloroglucinol test when tested according to ASTM D 1030, X5 spot stains, and shall have a Kappa number of 5 or less when tested according to TAPPI T 236.

### **1.3 Impurities**

The stock must be free of metal particles, waxes, plasticizers, residual bleach, peroxide, sulfur (which will be less than 0.0008% reducible sulfur as determined by TAPPI T 406), and other components that could lead to the degradation of the folder itself, or the artifacts stored therein.

### **1.4 Metallic Impurities**

Iron must not exceed 150 ppm and copper shall not exceed 6 ppm when tested according to TAPPI T 266.

### **1.5 Optical Brighteners**

The stock must be free of optical brightening agents.

### **1.6 pH**

The stock must have a pH value within a range of 8.0 - 9.5 as determined by TAPPI T 509, cold extraction (modified by slurring sample pulp before measurement).

### **1.7 Alkaline Reserve**

The stock must contain an alkaline reserve with a minimum of 2% and a maximum of 5% calculated as CaCO<sub>3</sub> when tested according to TAPPI T 553 (modified by slurring sample pulp before measurement).

## **1.8 Sizing**

Only neutral or alkaline sizing shall be used. No alum rosin or rosin sizing should be used, as determined by TAPPI T 408.

## **2. Physical and Performance Requirements**

### **2.1 Thickness and Basis Weight**

The stock must meet the following minimum requirements for basis weight as determined by TAPPI T 410.

#### **2.1.1 10 pt. Card**

The minimum basis weight should be 145 lbs/ 3,000 ft<sup>2</sup>

### **2.2 Color**

The color of the stock should be tan, cream, or buff, or will be specified on the purchase order. The color must not be so dark that it obscures color-dependent test evaluations, e.g., spot stain tests.

### **2.3 Color Bleeding**

The color must show no bleeding when soaked in distilled water for 48 hours while held under suitable weight in contact with white bond paper. The color must not rub off.

### **2.4 Color Retention**

The color of the stock must not change more than 5 points of brightness as measured by directional reflectance at 457 nm (TAPPI T 452), when exposed 24 hours to a Xenon arc lamp in an Atlas Weatherometer under the following conditions: Irradiance Level: 1.0 watts/m<sup>2</sup> at 420 nm. Inner filter: Borosilicate glass. Outer filter: clear soda lime glass. Black panel temperature: 50°C. Wet bulb depression: 8.5°C.

### **2.5 Photographic Activity Test**

The stock must pass the Photographic Activity Test (P.A.T.), meeting the criteria stipulated in sections 5.3, 6.3, and 7.2 of ISO 18916. Vendors may wish to confirm that their products pass the P.A.T. before submitting them to the Library of Congress for evaluation. The vendor may wish to send samples to the Image Permanence Institute (Rochester Institute of Technology/IPI, 70 Lomb Memorial Drive, Rochester, NY 14623-5604; Tel: 585-475-5199), or other testing laboratory, to determine conformance prior to submission.

### **2.6 Surfaces and Smoothness**

The surfaces of the stock must be free of fingerprints, dirt, bubbles, knots, shives and other imperfections. The stock should be smooth, e.g., calendered, hot-rolled, and/or water polished. The smoothness of the stock must be within the range of 175 to 220 Sheffield units, when tested according to TAPPI T 538.

### **2.7 Creases and Folds**

The stock must not fray, crack or split when folded and/or creased.

## **2.8 Folding Endurance**

The stock must meet the following minimum requirements for fold endurance in the machine direction. Tests will be conducted according to TAPPI T 511, after conditioning according to TAPPI T 402, using a 1 kg load.

### **2.8.1 10 pt Card**

The minimum fold endurance must be not less than 750 double folds.

## **2.9 Abrasion**

The outer surfaces of the stock must show a loss of less than 2% in weight when tested with a #CS10 wheel and 100 wear cycles according to TAPPI T 476.

## **2.10 Stiffness**

The stock must meet the following minimum requirements for stiffness. Test will be conducted according to TAPPI T 489, after conditioning by TAPPI method T 402.

### **2.10.1 10 pt. Card**

The minimum internal stiffness must be not less than 80 Taber units in the machine direction and 30 in the cross direction.

## **2.11 Adhesive**

If an adhesive is required, it must not soften or run. The adhesive must not cause the stock to become transparent or alter the color of the stock. The adhesive must not yellow, discolor, or fail (causing delamination) over time. The adhesive should not contain sulfur, iron, copper or other ingredients that may be detrimental to photographic materials. The adhesive should not contain or generate oxidants. Pressure-sensitive or rubber-based adhesives are not acceptable. When used, the adhesive must not extend beyond the joined area.

## **3. Product Requirements**

### **3.1 Construction**

The fold should be in the longer of the two dimensions of the expansion folder. The grain (machine direction) of the folder stock must run perpendicular to the fold. The folder must have an accordion expansion pleat on bottom and sides. The top corners of the front and back panels and the corners of seams should be rounded. The reinforced tab must be evenly adhered to the back panel, and fold to the inside. The expansion folder must be constructed with seams of folded flaps adhered to the outer side.

### **3.2 Workmanship**

The folders must be cut straight with squared sides. The sizes must be accurate. The edges must be smooth and even and meet exactly. There must be minimal planar distortion upon visual inspection. The seams must be smooth and flat with no puckering. The adhesive must not extend beyond the joined area.

### **3.3 Dimensions**

Dimensions will be specified on the purchase order. The allowable tolerance for each dimension is  $\pm 1/16$  inch.

#### 3.3.1 Folder sizes – L x W

Letter size – 12 1/4 x 10 1/4

Legal size – 15 1/4 x 10 1/4

#### 3.3.2 Expansion pleat

The expansion pleat on bottom and sides should be 1 1/2 inch.

#### 3.3.3 Full drop

The full drop for all folders should be 1 inch.

#### 3.3.4 Reinforced tab

The height of the reinforced tab should be a minimum of 1 1/8 inch.

### **3.4 Thickness**

Folders should be constructed of 10 pt card stock.

### **3.5 Marking**

Each folder must be marked with the name of the manufacturer, year of manufacture, and the actual pH.

#### 3.5.1 Placement and Size

The identifying information must not be larger than 2 1/2 inches long and 1 1/2 inches high. It should be centered on the back flap of each folder.

#### 3.5.2 Marking Method

The information can be stamped in ink or embossed.

##### 3.5.2.1 Ink Stamping

The stamping must be done on the outside of the folder. The ink must pass the Photographic Activity Test as described in ISO 18916. The ink must not smear, fade, or rub off after drying. The ink must not run, bleed through, or transfer to other materials if it becomes wet. There must be no ink on the interior of the folder.

##### 3.5.2.2 Embossing

The embossing must be done such that the raised text is to the outside of the folder. The impression should be as light as possible while still being legible.

## **4. Packaging and Identification**

#### **4.1 Inner Packages**

Each package must plainly identify the type, size and number of items within, the name of the supplier or manufacturer, year of manufacture, and manufacturing run or batch number.

#### **4.2 Outer Package**

The items must be packed in standard commercial containers that are constructed to ensure that they arrive at the Library of Congress in dry, undamaged condition. The outside of each container must be identified by type, size and number of items within; manufacturing run or batch number; LC Purchase Order / Contract number and line number.

### **5. Compliance with Specification**

#### **5.1 Quality Assurance Testing**

The Library of Congress has the right to perform any of the tests set forth in the specification where such tests are deemed necessary to ensure that supplies conform to prescribed requirements.

#### **5.2 Sampling**

To sample for testing, shipments will be sampled according to ANSI/ASQ Z1.4, inspection level S-2, AQL 2.5%.

#### **5.3 Methods**

Tests will be conducted in accordance with specified test methods of the American National Standards Institute (ANSI), the American Society for Testing and Materials (ASTM), the Technical Association of the Pulp and Paper Industry (TAPPI), and the International Organization for Standardization (ISO). Publications describing these tests may be ordered directly from the technical associations, their websites, or other on-line standards vendors.

#### **5.4 Acceptance**

Materials will be accepted when the Library of Congress has ascertained that the products comply with all parts of the specification. A quick reference table of the physical and chemical requirements and test methods used to ascertain compliance is provided in section 5.5.

**FAILURE TO MEET ANY PART OF THE SPECIFICATION WILL BE CAUSE FOR REJECTION**

## 5.5 Table of Physical and Chemical Requirements and Test Methods

Property	Requirement	Test Method
Lignin	Negative / Kappa 5	ASTM D 1030, X5 or TAPPI 236
Reducible Sulfur	< 0.0008%	TAPPI T 406
Iron	≤ 150 ppm	TAPPI T 266
Copper	≤ 6 ppm	TAPPI T 266
pH	8.0 – 9.5	TAPPI T 509, cold extraction, slurried pulp
Alkaline Reserve	2 – 5%	TAPPI T 553, slurried pulp
Alum Rosin Sizing	Negative	TAPPI T 408
P.A.T.	Pass	ISO 18916
Basis Weight	10 pt: 145 lbs./3,000 ft <sup>2</sup>	TAPPI T 410
Folding Endurance	10 pt: 750 MD	TAPPI T 511
Color Bleeding	No bleed in 48 hours	See section 2.3
Color Retention	≤ 5 pts	TAPPI T 452
Smoothness	175-220 Sheffield	TAPPI T 538
Abrasion	≤ 2%	TAPPI T 476
Stiffness	10 pt: 80 MD, 30 CD	TAPPI T 489

## Configuration Management

Date	Revision History
3-Apr-2003	Initial release of document on website, html format.
19-Jan-2011	Revised and reformatted for release as PDF document.